



JK PAPER LTD.

Creating lasting impressions

JK CEDAR

Technical Specifications

| Sl. No | Particulars | Unit | JK CEDAR | JK CEDAR |
|--------|----------------------|------------|------------|------------|
| | | | 80 | 100 |
| 1 | Substance | Gsm | 80+/- 1.5 | 100+/- 2.5 |
| 2 | Caliper | Micron | 90+/- 2 | 112+/- 2 |
| 3 | Breaking length | Metre | 4500 ± 500 | 4500 ± 500 |
| 4 | Tear Factor | -- | 65 ± 5 | 65 ± 5 |
| 5 | Sizing | Gsm | 28 ± 2 | 28 ± 2 |
| 6 | Moisture | % | 4.0 ± 0.5 | 4.0 ± 0.5 |
| 7 | Roughness (Bendsten) | Ml. / Min. | 70 Max | 70 Max |
| 8 | Wax Pick(Min) | No. | 12A | 12A |
| 9 | Brightness | % ISO | 96 +/- 1 | 96 +/- 1 |
| 10 | Opacity (Min) | % ISO | 94 | 94 |